



018	★★★★ ■ ▼ gr.1	 Titanium White Zinc Oxide PW4 Titanium Dioxide PW6	106	★★★★ ■ ▼ gr.2	 Naples Yellow Reddish Zinc Oxide PW4 Titanium Dioxide PW6 Anthraquinone P043	178	★★★★ □ gr.2	 Permanent Madder Deep Quinacridone PV19 Quinacridone PR206 Dioxazine PV23	276	★★★★ □ gr.1	 Pozzuoli Earth Synthetic Iron Oxide PR101 Natural Earth PR101 Calcined Natural Earth PB7
019	★★★★ ■ ▼ gr.2	 Titaniumzinc White Zinc Oxide PW4 Titanium Dioxide PW6	107	★★★★ ■ gr.2	 Naples Yellow Deep Zinc Oxide PW4 Synthetic Iron Oxide PY42 Arylide Yellow PY97	214	★★★★ ■ gr.2	 Quinacridone Rose Light Zinc Oxide PW4 Quinacridone PR122	278	★★★★ □ ▼ gr.1	 Burnt Sienna Original Natural Earth calcinata PB7
020	★★★★ □ ▼ gr.2	 Zinc White Zinc Oxide PW4 Titanium Dioxide PW6	110	★★★★ □ ▼ gr.2	 Permanent Orange Benzimidazolone P062 Anthraquinone P043	226	★★★★ ■ gr.3	 Cadmium Red Light Cadmium Sulphoselenide PR108	284	★★★★ □ gr.2	 Vermilion Light (Hue) Benzimidazolone P036 Pyrrole-pyrrole PR254
026	★★★★ ■ ▼ gr.2	 Super Rapid White Zinc Oxide PW4 Titanium Dioxide PW6	111	★★★★ □ gr.2	 Permanent Yellow Light Arylide Yellow PY97 Titanium Dioxide PW6	228	★★★★ ■ ▼ gr.3	 Cadmium Red Medium Cadmium Sulphoselenide PR108	285	★★★★ □ ▼ gr.2	 Vermilion Deep (Hue) Pyrrole-pyrrole PR254 Quinacridone PV19
075	★★★★ ■ gr.2	 Brilliant Yellow Light Zinc Oxide PW4 Benzimidazolone PY175	112	★★★★ □ gr.2	 Permanent Yellow Lemon Benzimidazolone PY175	232	★★★★ ■ gr.3	 Cadmium Red Deep Cadmium Sulphoselenide PR108	286	★★ □ gr.1	 Cinnabar Green Light Hansa Yellow GPY1 Phthalocyanine BetaPB15:3
076	★★★★ ■ gr.2	 Brilliant Yellow Deep Zinc Oxide PW4 Isoindoline PY139 Arylide Yellow PY97	114	★★★★ □ gr.1	 Permanent Yellow Deep Arylide Yellow PY97 Isoindoline PY139 Titanium Dioxide PW6	248	★★★★ ■ gr.1	 Mars Red Synthetic Iron Oxide PR101	287	★★ □ gr.1	 Cinnabar Green Yellowish Hansa Yellow GPY1 Sodium Polysulphide-Aluminosilicate PB29
080	★★★★ ■ gr.3	 Cadmium Orange Cadmium Sulphide PY35	116	★★★★ □ ▼ gr.2	 Primary Yellow Arylide Yellow PY97 Benzimidazolone PY175	249	★★★★ □ gr.2	 Permanent Red Orange Anthraquinone P043	288	★★ □ gr.1	 Cinnabar Green Deep Hansa Yellow GPY1 Phthalocyanine Alpha PB15:1 Benzimidazolone P036
081	★★★★ ■ gr.3	 Cadmium Yellow Light Cadmium Sulphide PY35	131	★★★★ □ ▼ gr.1	 Yellow Ochre Natural Iron OxidePY43 Synthetic Iron Oxide PY42 Zinc Oxide PW4	251	★★★★ □ gr.2	 Permanent Red Light Benzimidazolone P036 Pyrrole-pyrrole PR254	290	★★★★ □ gr.1	 Green Lake Arylide Yellow PY97 Chlorinated Phthalocyanine PG7 Phthalocyanine BetaPB15:3
082	★★★★ ■ gr.3	 Cadmium Yellow Lemon Cadmium Sulphide PY35	132	★★★★ □ gr.1	 Yellow Ochre Light Natural Iron OxidePY43 Titanium Dioxide PW6 Synthetic Iron Oxide PY42	253	★★★★ □ gr.2	 Permanent Red Deep Quinacridone PV19 Pyrrole-pyrrole PR254	296	★★★★ □ ▼ gr.1	 Green Earth Natural Earth PG23 Chlorinated Phthalocyanine PG7
084	★★★★ ■ gr.3	 Cadmium Yellow Deep Cadmium Sulphide PY35	134	★★★★ □ gr.1	 Golden Ochre Natural Iron OxidePY43 Synthetic Iron Oxide PY42 Zinc Oxide PW4	256	★★★★ □ ▼ gr.2	 Primary Red - Magenta Quinacridone PR122	307	★★★★ ■ ▼ gr.3	 Cadmium Green Cadmium Sulphide PY35 Chlorinated Phthalocyanine PG7
098	★★★★ □ gr.1	 Indian Yellow Arylide Yellow PY97 Anthraquinone P043	161	★★★★ □ ▼ gr.1	 Raw Sienna Original Natural Earth PB7	258	★★★★ □ gr.3	 Quinacridone Red Quinacridone PR209	321	★★★★ □ ▼ gr.2	 Phthalo Green Chlorinated Phthalocyanine PG7
105	★★★★ ■ ▼ gr.3	 Naples Yellow Light Zinc Oxide PW4 Arylide Yellow PY97 Synthetic Iron Oxide PY42	167	★★★★ □ ▼ gr.2	 Permanent Carmine Quinacridone PV19 Quinacridone PR206	262	★★ ■ gr.1	 Venetian Red Synthetic Iron Oxide PY42 Calcined Natural Earth PB7 Synthetic Iron Oxide PR101	336	★★★★ ■ gr.2	 Chrome Oxide Green Chromium Oxide PG17

339 ★★★ ▣ gr.2

Permanent Green Light
Benzimidazolone PY175
Chlorinated Phthalocyanine PG7
Titanium Dioxide PW6

340 ★★★ ▣ gr.1

Permanent Green Deep
Chlorinated Phthalocyanine PG7
Phthalocyanine Alpha PB15:1
Benzimidazolone PY175

356 ★★★ ▣ gr.3

Emerald Green
Zinc Oxide PW4
Benzimidazolone PY175
Phthalocyanine Beta PB15:3

358 ★★★ ▣ ▼ gr.2

Sap Green
Synthetic Iron Oxide PR101
Chlorinated Phthalocyanine PG7

368 ★★★ ▣ gr.3

Cerulean Blue
Cobalt Aluminium-Chromium Oxides PB36
Phthalocyanine Alpha PB15:1

370 ★★★ ▣ ▼ gr.1

Cobalt Blue Light (Hue)
Sodium Polysulphide-Aluminosilicate PB29
Zinc Oxide PW4
Titanium Dioxide PW6

371 ★★★ ▣ gr.2

Cobalt Blue Deep (Hue).
Sodium Polysulphide-Aluminosilicate PB29
Zinc Oxide PW4
Phthalocyanine Alpha PB15:1

391 ★★★ ▣ gr.1

Ultramarine Light
Sodium Polysulphide-Aluminosilicate PB29

392 ★★★ ▣ ▼ gr.1

Ultramarine Deep
Sodium Polysulphide-Aluminosilicate PB29

400 ★★★ □ ▼ gr.2

Primary Blue - Cyan
Phthalocyanine Beta PB15:3
Phthalocyanine PB16

402 ★★★ ▣ ▼ gr.1

Prussian Blue
Ferric Ferrocyanide PB27

405 ★★★ ▣ gr.3

King's Blue Light
Zinc Oxide PW4
Cobalt Aluminium-Chromium Oxides PB36

408 ★★★ ▣ gr.2

Turquoise Blue
Zinc Oxide PW4
Phthalocyanine PB16
Chlorinated Phthalocyanine PG7

410 ★★★ ▣ gr.2

Phthalo Blue Green
Chlorinated Phthalocyanine PG7
Phthalocyanine Beta PB15:3

414 ★★★ ▣ ▼ gr.2

Sky Blue
Zinc Oxide PW4
Phthalocyanine Beta PB15:3

448 ★★★ ▣ ▼ gr.2

Cobalt Violet (Hue)
Quinacridone PV19
Dioxazine PV23

463 ★★★ ▣ ▼ gr.2

Permanent Violet Blueish
Dioxazine PV23

465 ★★★ ▣ gr.2

Permanent Violet Reddish
Quinacridone PV19
Dioxazine PV23

484 ★★★ ▣ ▼ gr.1

Vandyke Brown
Calcined Original Natural Earth PBr7
Bone Black PBk9
Carbon Black PBk7

488 ★★ ▣ gr.1

Brown Stil de Grain
Naphthol AS PR146
Diarylide Yellow PY833
Chlorinated Phthalocyanine PG7

490 ★★★ ▣ gr.1

Cassel Earth
Calcined Original Natural Earth PBr7
Bone Black PBk9
Calcined Natural Earth PBr7

492 ★★★ ▣ ▼ gr.1

Burnt Umber
Calcined Natural Earth PBr7

493 ★★★ ▣ ▼ gr.1

Raw Umber
Natural Earth PBr7
Chromium Oxide PG17

514 ★★★ ▣ gr.1

Payne's Grey
Sodium Polysulphide-Aluminosilicate PB29
Bone Black PBk9

535 ★★★ ▣ ▼ gr.1

Ivory Black
Bone Black PBk9
Carbon Black PBk7

540 ★★★ ▣ gr.1

Mars Black
Synthetic Iron Oxide PBk11

003 ★★★ □ gr.2

Silver
Titanium Dioxide+Mica+
Synthetic Iron Oxide

137 ★★★ □ gr.2

Light Gold
Titanium Dioxide+Mica+
Synthetic Iron Oxide

151 ★★★ □ gr.2

Deep Gold
Titanium Dioxide+Mica+
Synthetic Iron Oxide